



Triathlon 800

All Purpose Rubber Flooring

PRODUCT SPECIFICATIONS

Technical Data	Standard/Norms	Data
Composition		Rubber with EPDM content, up to 100%
Style		Interlocking & Square Edge Tile
Overall Thickness		1/4" (6mm), 5/16" (8mm), 3/8" (10mm),
Size		38"x38" Square; 37"x37" Interlocking
Shore Hardness	ASTM D2240	64 Indentation Hardness
Density Foam Test	ASTM D3676	66.0 lbs/cubic foot
Tensile Strength	ASTM D412	290.2 lbs/square inch
Taber Abrasion (H-22)	ASTM C501	0.8% weight loss
Flammability (Critical Radiant)	ASTM E648	Class 2
Compression Set Under Force	ASTM D395B	96.3% recovered
Static Load	ASTM F970	0.000 inches (0.0%) residual compression
Static Coefficient of Friction	ASTMD2047	Dry: 1.04; Wet: 1.05
Material Emissions - VOC	ASTM D5116	Pass
Electrical Resistance (Burroughs)	ASTM F150	Surface to Surface: 10 ¹⁰ ohms average.
Short Term & Residual	ASTM F1914	Short Term: 0.25 inches (6.0% loss; Residual:
Resistance to Chemicals	ASTM F925	No Change after 24 hours